



Flexible & Elastomeric	Product	Use	Compatible Printers	Color	Viscosity (CPs)	Hardness (Shore)	Tensile Strength (MPa)	Tensile Elongation (%)	Tear Strength (N/mm)	Resilience (%)	Compression Set (%)	Note
	FP-1000	Midsole & Others	Phrozen, Anycubic, YDM, Crealty	White, Black, Natural	1200	70 A	9	120	16.5	12	54	2 Parts, Heat cure
	FP-1000M	Midsole & Others	Phrozen, Anycubic, YDM, Crealty	White, Black, Natural	300	70 A	10	150	16	10	30	2 Parts, Heat cure
	FP-1000M2	Midsole & Others	Phrozen, Anycubic, YDM, Crealty	White, Black, Natural	400	70 A	5	240	18	10	20	2 Parts, Heat cure, Moderate Pot Life
	FP-1000M3	Midsole & Others	Phrozen, Anycubic, YDM, Crealty	White, Black, Natural	500	65A	4	190	20	9	17	2 Parts, Heat cure, Long Pot Life
	FP-1025	Midsole & Others	Phrozen, Anycubic, YDM, Crealty	White, Black, Natural	500	75 A	10	140	15	10	40	2 Parts, Heat cure
	FP-1064	Midsole & Others	Phrozen, Anycubic, YDM, Crealty	White, Black, Natural	350	60 A	4	153	12	33	17	2 Parts, Heat cure, Moderate Pot Life
	FP-3000	Midsole & Others	Phrozen, Anycubic, YDM, Crealty	White, Black, Natural	900	75 A	14	240	35	15	32	2 Parts, Heat cure
	FP-2074	Midsole & Others	Phrozen, Anycubic, YDM, Crealty	White, Black, Natural	700	60 A	3	285	13	8	5	1 Part
Water Clean	Product				Viscosity (CPs)	Hardness (Shore)	Tensile Strength (MPa)	Tensile Elongation (%)	Softening Point (°C)			
	GPWW-2000-1	General Purpose	Phrozen, Anycubic, YDM	Natural	460	85 D	45	4	80			
ABS-Like	Product				Viscosity (CPs)	Hardness (Shore)	Tensile Strength (MPa)	Tensile Elongation (%)	Softening Point (°C)			
	ABS-1005		Asiga, Phrozen, Anycubic, YDM	Natural, Gray, White, Black, Beige	300	77 D	22	15	50			

	ABS-2000-1		Asiga, Phrozen, Anycubic, YDM	Natural	210	85 D	56	3	80			
<b>Dental Model</b>	<b>Product</b>				<b>Viscosity (CPs)</b>	<b>Hardness (Shore)</b>	<b>Flexural Strength (MPa)</b>	<b>Flexural Modulus (MPa)</b>	<b>Softening Point (°C)</b>			
	TM-3000	Model & Die	Asiga, Rapid Shape, MiiCraft,Dreve	Beige	120	80 D	36	1200	80			For DLP
	TM-1000M1	Model & Die	Nexa3D, Phrozen, Anycubic, YDM	Beige	120	80 D	77	2500	80			For LCD Fast Print
<b>Flame Retardant</b>	<b>Product</b>				<b>Viscosity (CPs)</b>	<b>Hardness (Shore)</b>	<b>Tensile Strength (MPa)</b>	<b>Tensile Elongation (%)</b>	<b>Softening Point (°C)</b>			
	FR-3000		Phrozen, Anycubic, YDM	White	330	90 D	25	1	200			Passed UL-94 V0